

DI-TAPES

PVC Tapes for Sealing Shuttering against Grout Loss

DESCRIPTION

A range of tapes specially selected for use in concrete construction to seal shuttering and moulds against grout loss.

These PVC tapes are also suitable for jointing DPM's in the approved manner, Line marking, jointing polythene for protection purposes.

The std grade is a cost effective tape with good adhesion, however if superior performance is required we would recommend the High Tack Version.

PROPERTIES

	Di-Tape Std	Di-Tape High Tack
Carrier	Yellow PVC film	0.12mm Yellow PVC
Adhesive	Rubber base	Rubber Base
Liner	None	None
Thickness	0.15mm	0.17mm
Max App. Temp.	50°C	50°C
Min App. Temp.	-5°C	-5°C
Adhesion To Steel	1.5 N/cm	1.75 N/cm
Elongation at break	150%	175%
Tensile strength	28 N/cm	2.7 daN/CM

APPLICATION

It is essential, as with all pressure sensitive tapes, that the surfaces to which the tape is applied be clean, dry and free of grease and oil.

COVERAGE

Not applicable

STORAGE & HANDLING

One year stored at 21°C (70°F), 50% relative humidity, out of direct sunlight.

PACKAGING & TRANSPORT

Rolls of 50mm wide x 33m long

Di-Tape Std is packaged in boxes of 24 rolls

Di-Tape High Tack is Packaged in boxes of 18 rolls

Not Regulated for Road Transport

HEALTH & SAFETY

Not Regulated

QUALITY ASSURANCE

Direct Chemicals is a firm of assessed capability. The Company's quality system conforms to BS EN ISO 9001:2000 and is assessed by QMS International PLC. Products are manufactured under quality assured schemes.



Direct Chemical products are guaranteed against defective materials and manufacture. Products are sold subject to the Direct Chemical Terms and Conditions of Sale, copies of which are available on request. Direct Chemicals endeavours to ensure that the above data and any further advice is correct, however Direct Chemicals can not accept liability for the use to which products are put or the way in which they are used. All recommendations stated by the company are made in good faith. Recommendations do not over-ride the basic obligation of the user to satisfy themselves at all times as to suitability of the product for their particular application.



Direct Chemicals
PO BOX 3786, Bracknell
Berkshire, RG12 7TH
Tel: 0118 989 2666
Fax: 0118 989 0929
Email: sales@dichem.co.uk
Web: www.dichem.co.uk

